

EMU 3000 SERIES COLORANTS



CHARACTERISTICS : aqueous pigment dispersions realized in proper wetting - dispersant agents, exempt from binders. Apeo free. VOC free.

COMPATIBILITY : all Water-Borne decorative systems such as enamels, emulsion paints, and high pH WB coating products like silicate / lime paints (see also FASTNESS CHART).

APPLICATION : WB systems in the decorative/architectural market segment.

FULL SHADE	REDUCED SHADE	CODE	DESCRIPTION	COLOR INDEX	Specific Weight gr./l. $\pm 5\%$	Pigment Content (% weight) $\pm 5\%$
		301 M	WHITE	PW 6	1660	52
		302 M	YELLOW OXIDE	PY 42	1650	50
		3060	MONOAZO YELLOW	PY 74	1120	25
		336 A	GREENISH YELLOW	PY 184	1700	50
		3306	FAST ORGANIC YELLOW	PY 154	1130	25
		3508	ORGANIC ORANGE	PO 74	1100	20
		3511	MAGENTA	PR 122	1080	20
		3312	FAST ORGANIC RED	PR 168	1200	29
		312 I	ORGANIC RED	PR 112	1120	23
		313 M	RED OXIDE	PR 101	1620	45
		3516	VIOLET	PV 23	1080	16
		3517	COBALT BLUE	PB 28	1850	60
		3019	BETA PHTHALO BLUE	PB 15.3	1100	21
		3020	PHTHALO GREEN	PG 7	1180	23
		321 M	GREEN OXIDE	PG 17	1520	38
		325 M	BLACK OXIDE	PBk 11	1710	50

Values are to be considered as nominal and should be treated as a guideline. We suggest to perform always a preliminary compatibility test. The producer reserves the right to modify at any time these parameters, without giving advance notice, in order to respect the tolerance of colorimetric standards.

The colours here represented are by way of example, in terms of colour strength and shade. Colours might differ from real product depending on the printer and video installed.

Colorificio Migliavacca 1919 Srl - Via dell'industria, 20 - 24126 BERGAMO (ITALY) - Tel +39 035.243.879
www.colorificiomigliavacca.it - E-mail: info@colorificiomigliavacca.it
 member of **AMERICAN COLORS INC. (USA)**