

SOL 9000 SERIES COLORANTS



CHARACTERISTICS : pigment dispersions realized in aldehyde resin and proper polymeric wetting agents.
Aromatic solvents free.

COMPATIBILITY : 1K or 2K solvent based coating systems.

APPLICATION : Specific for:

- Industrial coatings
- Wood coatings
- Metal coatings
- Architectural coatings

| FULL SHADE | REDUCED SHADE | CODE | DESCRIPTION | COLOR INDEX | Pigment Content (% weight) ±5% | HIGH Q 16 pastes SYSTEM ±5% |
|------------|---------------|-------|------------------------|-------------|--------------------------------|-----------------------------|
| | | 9001 | WHITE | PW 6 | 65 | • |
| | | 9002 | YELLOW OXIDE | PY 42 | 53 | • |
| | | 906 A | GREENISH YELLOW | PY 184 | 50 | • |
| | | 906 I | ORGANIC MEDIUM YELLOW | PY 194 | 25 | • |
| | | 9006 | ORGANIC YELLOW | PY 74 | 20 | |
| | | 906 M | ORGANIC REDDISH YELLOW | PY 139 | 25 | • |
| | | 908 B | ORGANIC ORANGE | PO 36 | 25 | • |
| | | 9010 | MANGANESE RED | PR 52:2 | 20 | |
| | | 911 R | MAGENTA | PR 122 | 14 | • |
| | | 912 D | FAST ORGANIC RED | PR 254 | 25 | • |
| | | 912 R | ORGANIC RED | PR 170 | 25 | |
| | | 913 M | RED OXIDE | PR 101 | 60 | • |
| | | 9015 | RED VIOLET | PV 19 | 18 | • |
| | | 9016 | VIOLET | PV 23 | 10 | • |
| | | 917 M | ULTRAMARINE BLUE | PB 29 | 50 | • |
| | | 918 A | PHTHALO BLUE ALPHA | PB 15:2 | 18 | • |
| | | 918 B | PHTHALO BLUE BETA | PB 15:4 | 19 | • |
| | | 9020 | PHTHALO GREEN | PG 7 | 20 | • |
| | | 9023 | BLACK | PBk 7 | 20 | • |
| | | 9024 | DEEP BLACK | PBk 7 | 10 | |

The colours here represented are by way of example, in terms of colour strength and shade. Colours might differ from real product depending on the printer and video installed. The producer reserves the right to modify at any time these parameters, without giving advance notice, in order to respect the tolerance of colorimetric standards.

Data are based on information provided by pigment producers. Values are to be considered as nominal and should be treated as guideline without guarantee. We suggest to perform always a preliminary compatibility test, since usage is beyond our control.

Colorificio Migliavacca 1919 Srl - Via dell'industria, 20 - 24126 BERGAMO (ITALY) – Tel +39 035.243.879
www.colorificiomigliavacca.it - E-mail: info@colorificiomigliavacca.it
member of **AMERICAN COLORS INC. (USA)**